Alloy 625

This alloy has outstanding resistance to pitting and crevice corrosion as well as good resistance to intergranular attack. It also is almost totally resistant to chloride-induced stress corrosion cracking. With these properties the alloy has extremely high resistance to attack by a wide range of media and environments including nitric, phosphoric, sulphuric and hydrochloric acids, as well as alkalis and organic acids in both oxidising and reducing conditions. Alloy 625

has virtually no corrosive attack in marine and industrial atmospheres with extremely good resistance to seawater, even at elevated temperatures.

It is an excellent choice for applications that require high corrosion-fatigue strength or high tensile strength applications, creep and rupture strength and weldability.

Typical applications include:

- Sour Gas Service
- Engine exhaust systems
- Fuel and Hydraulic Lines
- Distillation columns and chemical transfer lines
- Nuclear water reactors

Alloy 625 is one of our best seller materials. It is one of the preferred alloy in a wide range of sour gas applications.



| Typical Composition | | |
|-------------------------|--------------|--|
| Element | Weight (%) | |
| Carbon | 0.1 max | |
| Manganese | 0.5 max | |
| Chromium | 20.0 to 23.0 | |
| Nickel | 58.0 min | |
| Molybdenum | 8.0 to 10.0 | |
| Iron | 5.0 max | |
| Columbium + Tantalum | 3.15 to 4.15 | |
| Titanium | 0.4 max | |
| Aluminium | 0.4 max | |
| Cobalt | 1.0 max | |

| Typical Specifications | | |
|------------------------|----------------------------|--|
| Product | Standard | |
| Bar | ASTM B446 | |
| Forging | ASTM B564 | |
| Tube | ASTM B444 | |
| Other | NACE MR0175 NACE MR0103 | |
| UNS No. | N06625 | |

Refer to page 9 for product availability.

Tubing Specification: High Quality, Fully Annealed, Alloy 625 Tubing to ASTM B444 Grade 2 UNS N06625. Recommended Tube Hardness 85 HRB. Maximum Permissible Hardness 93 HRB.

| Table 9 | Alloy 625 | | | |
|--------------|------------------------|-------|-------|--|
| Tube | Wall Thickness, inches | | | |
| O.D. Size | 0.035 | 0.049 | 0.065 | |
| 1/4 | 6800 | | | |
| 3/8 | 4400 | 6400 | 8700 | |
| 1/2 | | 5000 | 6800 | |
| 3/4 | | | 4400 | |

| Working pressure is measured | in | 'psig' | |
|------------------------------|----|--------|--|
|------------------------------|----|--------|--|

No data/Not recommended/No solution

| Table 10 | Alloy 625 | | | Metric | |
|--------------|--------------------|-----|-----|--------|-----|
| Tube O.D. | Wall Thickness, mm | | | | |
| Size | 0.8 | 1 | 1.2 | 1.5 | 1.8 |
| 6 | 440 | 570 | | | |
| 10 | 260 | 330 | 400 | 510 | 630 |
| 12 | | | 330 | 420 | |

Working pressure is measured in 'bar'

| Recommended for all services - standard assembly |
|---|
| Recommended for all services - Use pre-assembly tool |
| Recommended for all services - Use 'Hyferset' pre-assembly tool |
| |